




1K Multi Plastic Primer

One component ready for use primer for promoting adhesion on plastic parts.



RTS 1K Multi Plastic Primer




**Spray gun set-up:
1.3-1.4 mm**



**Application pressure:
1.8-2.2 bar**




1 x 1 coat



Between coats N.A.

**Recoatable within:
20 min.-24 hours at 20 °C**



Recoatable with:
Filler White / Grey / Black
Filler White / Grey / Black Aerosol
Hidrosonne EVO





Additional Information

Substrates Suitable for all plastic car body parts available to date, with the exception of parts made of pure PE (polyethylene)

Shelflife 2 years

Note Minimum application temperature 15°C

2004/42/IIb(e)(840)772

The EU limit value for this product (product category: IIb(e)) in ready to use form is 840 gram/liter of VOC.
The VOC content of this product in ready to use form is max. 772 gram/liter.

Hella Ltd
Unit 6, Appletree Industrial Estate, Appletree Road
OX17 1LL Chipping Warden, Chipping Warden, Oxon
Tel. +44 (0) 1295 662400
Fax +44 (0) 800 783 2571

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to HELLA S.A.
www.hella.com